

9-20-00

A

09/18/00
jc813 U.S. PTO


WILLIAMS, MORGAN & AMERSON, P.C.

7676 HILLMONT, SUITE 250, HOUSTON, TX 77040
(713) 934-7000 FAX (713) 934-7011

Danny L. Williams
Terry D. Morgan
J. Mike Amerson
Kenneth D. Goodman
Barbara S. Kitchell, Ph.D.
Jeffrey A. Pyle
Randall C. Furlong, Ph.D.

Scott F. Diring*
George J. Oehling*
Shelley P.M. Fussey, Ph.D.*
Mark D. Moore, Ph.D.*
Carolanne M. King*
Louis H. Iselin, Ph.D.*
Raymund F. Eich, Ph.D.*

*Patent Agent

EXPRESS MAIL MAILING LABEL
NUMBER: EL522493685US
DATE OF DEPOSIT: SEPTEMBER 18, 2000
I hereby certify that this paper or fee is being deposited with the United States Postal Service with sufficient postage "EXPRESS MAIL POST OFFICE TO ADDRESSEE" service under 37 C.F.R. 1.10 on the date indicated above and is addressed to: Assistant Commissioner for Patents, Washington D.C. 20231.
 Carol Porter

jc542 U.S. PTO
09/664993
09/18/00

RAYMUND F. EICH, Ph.D.
(713) 934-4065

September 18, 2000

FILE 2039 006100

BOX PATENT APPLICATION
Assistant Commissioner for Patents
Washington, D.C. 20231

RE: *U.S. Patent Application Entitled*
OXYGEN SCAVENGERS WITH REDUCED OXIDATION PRODUCTS
FOR USE IN RIGID BEVERAGE AND FOOD CONTAINERS
Inventors: Kevin Cai/Ta Yen Ching/Hu Yang
Client Reference: T-5853

Sir:

Transmitted herewith for filing are a 38-page patent specification with 17 claims, a title page, and an abstract.

All correspondence, notices, official letters and other communications should be directed to Raymund F. Eich, Williams, Morgan & Amerson, P.C., 7676 Hillmont, Suite 250, Houston, TX 77040, and all telephone calls should be directed to Raymund F. Eich at (713) 934-4065.

Please note that this application is filed without an inventor Declaration and Assignment, a Declaration Claiming Small Entity Status, a Power of Attorney, and filing fees. Pursuant to 37 C.F.R. § 1.53(b) and (f), Applicants request that the Patent and Trademark Office accept this

WILLIAMS, MORGAN & AMERSON, P.C.


Assistant Commissioner for Patents
September 18, 2000
Page 2

application and accord a serial number and filing date as of the date this application is deposited with the U.S. Postal Service for Express Mail. Further, Applicants request that the NOTICE OF MISSING PARTS-FILING DATE GRANTED pursuant to 37 C.F.R. § 1.53(f) be sent to the undersigned Applicants' representative.

Pursuant to 37 C.F.R. § 1.10, Applicants request that the Patent and Trademark Office accept this application and accord a serial number and filing date as of the date this application is deposited with the U.S. Postal Service for Express Mail.

Please date stamp and return the enclosed postcard to evidence receipt of these materials.

Respectfully submitted,



Raymund F. Eich
Reg. No. 42,508

AGENT FOR APPLICANTS


RFE:cm
Enclosure

008160-8664950

for

by

Kevin Cai
Ta Yen Ching
Hu Yang



OXYGEN SCAVENGERS WITH REDUCED OXIDATION PRODUCTS FOR USE IN RIGID BEVERAGE AND FOOD CONTAINERS

This is a continuation-in-part application of U.S. Patent Application Serial No.
5 09/127,316 filed July 31, 1998.

FIELD OF THE INVENTION

The present invention relates to rigid polymeric food or beverage containers
comprising polyester such as polyester terephthalate or polyester naphthalate
10 and oxygen scavenging polymer.

BACKGROUND OF THE INVENTION

Multilayer rigid container structures, which utilize an oxygen scavenging
composition, are known. In the container wall, base polymers such as
15 polyethylene terephthalate have been used along with an oxygen scavenger.
The resulting multilayer package wall includes at least an oxygen scavenger
core layer as well as inner and outer layers having high oxygen barrier
qualities. The oxygen scavenger core layer is a combination of at least an
oxygen-scavenging polymer with post consumer-polyethylene terephthalate
20 (PC-PET). The inner and outer layers include at least oxygen barrier quality
PET.

Furthermore, multilayer plastic bottles having oxygen-scavenging capacity
sufficient to maintain substantially zero or near zero presence of oxygen in
25 the bottle cavity under specified storage conditions have also been disclosed.
The multilayer bottle wall has at least three layers. The inner and outer layers
are PET or another bottling polyester, which define the bottle cavity and the
outside skin of the bottle respectively. Between the inner and outer layers is
an oxygen scavenging copolyester layer.

Condensation copolymers used for making bottles with polyester such as PET or polyethylene naphthalate (PEN) have also been disclosed. The condensation copolymers comprise predominantly polyester segments and an oxygen-scavenging amount of polyolefin oligomer segments. The copolymers are preferably formed by transesterification during reactive extrusion and typically comprise about 0.5 to about 12 wt. % of polyolefin oligomer segments. In a preferred embodiment, a bottle is provided having a multilayer wall of at least three layers. The outer and inner layers are of unmodified PET and the oxygen scavenging layer in between the outer and inner layer is made of the condensation copolymers described above having an oxygen scavenging amount of polyolefin oligomers.

A transparent oxygen-scavenging article for packaging oxygen sensitive products is also known, the oxygen-scavenging article having a multilayered wall including at least three layers, an inner and outer layer of biaxially-oriented aromatic polyester polymers such as PET or PEN and an oxygen-scavenging aromatic ester polymer compatible with the polyester polymer. The oxygen-scavenging aromatic ester polymer must include ketone carbonyl groups to provide the oxygen-scavenging functionality and aromatic and ester groups for compatibility with the polyester.

PET containers have been disclosed that have a container wall of stretched plastic material with high oxygen barrier properties and an activating metal incorporated into the plastic material. The plastic material is PET in admixture with a polyamide and the metal is either added to the mixture or contained in one or both of the polymers.

A container containing at least one layer containing a plastics material and ions of at least one metal has also been disclosed. The plastics material in the layer consists of at least a partially split or degraded polyamide which has

increased sensitivity to reaction with oxygen in the presence of metal thus giving the layer improved oxygen barrier properties.

5 A container has been disclosed with a wall having high oxygen barrier properties comprising a molded polymer composition, the composition comprising a granular mixture of (1) a first polymer composition providing strength for the article and (2) a second polymer composition providing strength for the article and (2) a second polymer composition compatible with the first polymer composition. The second polymer composition is obtainable
10 by reacting a polyamide or copolyamide with a solution of a transition metal compound in a volatile solvent under refluxing conditions. The polymer of the first polymer composition can be any polymer and the metal of the metal compound reacted with the polyamide or copolyamide can be any transition metal. The amount of metal in the second polymer composition is at least
15 500 ppm.

A polymer material having increased sensitivity to reaction with oxygen has also been disclosed, the polymer material comprising a polyamide, which has been reacted with a nucleophilic reagent and possibly an activator. The
20 nucleophilic reagent is selected from the group consisting of compounds containing at least one hydroxyl group, compounds containing at least one alkoxide group, phosphate compounds, pyrophosphate compounds, polyphosphate compounds, salts of organic acids and copolymer of vinyl alcohol and ethylene. The activator is in the form of a hydrogen donor. A
25 process is also disclosed for producing the polymer material, which has increased sensitivity of reaction with oxygen. In the process, a polyamide reacts with the nucleophilic reagent under such conditions that the polymer material is obtained.

008160-864960

Such polymeric containers of PET, PEN and/or polyamide as described above utilize oxidizable components to react with and decrease the amount of oxygen in contact with oxygen sensitive materials packaged in containers. All of these oxidizable materials have the disadvantage of imparting unpleasant odor and/or taste to the packaged materials because of the byproducts given off during the oxidation of the oxidizable materials. Another problem is the uncontrolled oxidation fragmentation from the polymer backbone, which leads to chain secession, thus weakening the physical integrity of the multilayer container structures.

10

In contrast, the present invention achieves a rigid beverage and food container comprising PET and/or PEN, the container incorporating an oxygen scavenging component of cyclic olefin which does not give off odor and or taste as a result of its oxygen scavenging function. The oxidation also does not cause a change in molecular weight. This is because the cyclic olefin oxygen-scavenging component does not fragment as it oxidizes, thus avoiding the problem of imparting oxidation byproducts to the packaged material while maintaining the structural integrity.

20 Thus, the present invention overcomes, or at least reduces the effects of, one or more of the aforementioned problems.

Further aspects and advantages of the present invention will become apparent from the ensuing description, which is given by way of example only.

25

SUMMARY OF INVENTION

According to one aspect of the present invention, there are provided rigid containers containing oxygen scavenger compositions, said scavenger

polymeric backbone as a result of oxidation of the above compositions,
article, layer and process.

In yet another preferred embodiment of the invention, the transition metal
5 catalyst of the above oxygen scavenging composition, article of manufacture,
layer and process is a metal salt.

In still another preferred embodiment of the invention, the metal in the metal
salt of the above oxygen scavenging composition, article of manufacture,
10 layer and process is cobalt.

In still another preferred embodiment of the invention, the metal salt of the
above oxygen scavenging composition, article of manufacture, layer and
process is selected from the group consisting of cobalt neodecanoate, cobalt
15 2-ethylhexanoate, cobalt oleate and cobalt stearate.

In yet another preferred embodiment of the invention, the composition of the
above oxygen scavenging composition, article of manufacture, layer and
process further comprises at least one triggering material to enhance initiation
20 of oxygen scavenging.

In still another preferred embodiment of the invention, the triggering material
of the above oxygen scavenging composition, article of manufacture, layer
and process is a photoinitiator.

25

In yet another preferred embodiment of the invention, the molded or
thermoformed shape of the above article of manufacture is a bottle.

In still another preferred embodiment of the invention, the oxygen scavenging
30 layer is adjacent to one or more additional layers.

In still another preferred embodiment of the invention, at least one of the additional layers adjacent to the above layer is an oxygen barrier.

- 5 In still another preferred embodiment of the invention, the oxygen barrier of the above layer comprises a member of the group consisting of poly(ethylene-vinyl alcohol), polyacrylonitrile, poly(vinyl chloride), polyamides, poly(vinylidene dichloride), poly(ethylene terephthalate), silica, metal foil and metalized polymeric films.

10

In still another preferred embodiment of the invention, the one or more of said additional layer or layers of the above layer is coextruded with the above layer.

- 15 The present invention also relates to a rigid container for food or beverage, the container being molded from a resin comprising the above-described non-odorous oxygen scavenging polymer composition.

The present invention also relates to the above-described rigid container

- 20 further comprising a tinted ultraviolet protection layer, which may or may not be the food contact layer, located between the layer comprising the non-odorous oxygen scavenging composition and the inside of the rigid container.

In yet another more preferred embodiment of the rigid container comprises a

- 25 multilayered structure having one or more layers in addition to an oxygen scavenging layer, the other layer(s) being an aromatic polyester or copolyester selected from the group consisting of polyethylene terephthalate, polyethylene naphthalate, polypropylene terephthalate, polybutylene terephthalate, polyethylene isophthalate, polycyclohexanedimethanol

terephthalate, polybutylene naphthalate, polycyclohexanedimethanol naphthalate, and copolymers and blends thereof.

In still another more preferred embodiment, the composition of the resin of the
5 above-described rigid container is a single layer.

In yet another more preferred embodiment, the composition of the resin of the above-described rigid container is multilayered.

10 In yet another more preferred embodiment, the composition of the resin of the above-described rigid container comprises an outer air contact layer and an inner oxygen scavenging layer.

In still another more preferred embodiment, the outer air contact layer of the composition of the resin of the above-described rigid container comprises an oxygen barrier resin selected from the group consisting of polyethylene terephthalate, polyethylene naphthalate and a mixture of polyethylene terephthalate and polyethylene naphthalate.

20 In yet another more preferred embodiment, the composition of the resin of the above-described rigid container further comprises at least one of an inner food contact layer, a tie layer, and a tinted ultraviolet protection layer.

In still another more preferred embodiment, the inner food contact layer of the composition of the resin of the above-described rigid container comprises an oxygen barrier resin selected from the group consisting of polyethylene terephthalate, polyethylene naphthalate and a mixture of polyethylene terephthalate and polyethylene naphthalate.

In yet another more preferred embodiment, the oxygen scavenging of the composition of the resin of the above-described rigid container is initiated by moisture or actinic radiation.

- 5 In still another more preferred embodiment, the transition metal catalyst of the composition of the resin of the above-described rigid container is a metal salt.

In yet another more preferred embodiment, the metal in the metal salt of the transition metal catalyst of the composition of the resin of the above-
10 described rigid container is cobalt.

In still another more preferred embodiment, the metal salt of the transition metal catalyst of the composition of the resin of the above-described rigid container is selected from the group consisting of cobalt neodecanoate,
15 cobalt 2-ethylhexanoate, cobalt oleate and cobalt stearate.

In yet another more preferred embodiment, the composition of the resin of the above-described rigid container further comprises at least one triggering material to enhance initiation of oxygen scavenging.
20

In still another more preferred embodiment, the triggering material of the resin of the composition of the above-described rigid container is a photoinitiator.

In yet another more preferred embodiment, the photoinitiator of the resin of
25 the composition of the above-described rigid container has an ultraviolet absorption window above 320 nm.

In still another more preferred embodiment, the above-described rigid container is suitable for packaging oxygen sensitive drinks for extended
30 freshness and shelf life.

In yet another more preferred embodiment, the above-described rigid container is suitable for packaging beer, wine, fruit juice, or another oxygen sensitive drink.

5

DETAILED DESCRIPTION OF THE INVENTION

The present invention provides a rigid container for food or beverage, the container being molded from a resin comprising a non-odorous oxygen scavenging polymer composition having a polymer backbone and cyclic
10 olefinic pendant groups, alkyl acrylate pendant groups, or a combination thereof. Optionally, the composition further comprises linking groups linking the pendant groups to the polymer backbone.

The oxygen scavenging compositions are used in the preparation of rigid and
15 semi rigid packaging materials, containers and the like. Typical rigid and semi rigid articles include plastic, paper or cardboard cartons, bottles such as juice containers and beer containers, thermoformed trays or cups, with wall thicknesses generally greater than about 0.75 mil. The walls of such articles can comprise single or multiple layers of materials.

20

In many embodiments, the rigid container will comprise a multilayered structure having one or more barrier layers in addition to an oxygen scavenging layer, the barrier layer(s) being typically made from an aromatic polyester or copolyester, such as those selected from the group consisting of
25 polyethylene terephthalate, polyethylene naphthalate, polypropylene terephthalate, polybutylene terephthalate, polyethylene isophthalate, polycyclohexanedimethanol terephthalate, polybutylene naphthalate, polycyclohexanedimethanol naphthalate, poly(ethylene vinyl alcohol), polyacrylonitrile, polyvinyl chloride, poly(vinylidene dichloride), silica,
30 polyamides, nylon, MXD6, or copolymers or blends thereof.

008160" E664960

In one particularly illustrative embodiment, rigid containers are provided that comprise at least an outer layer, an inner layer and an oxygen scavenging layer between the inner and outer layers, wherein the oxygen scavenging layer is prepared from an oxygen scavenging composition disclosed herein and wherein the inner and outer layers of the rigid container are comprised of an aromatic polyester or copolyester, such as those selected from the group consisting of polyethylene terephthalate, polyethylene naphthalate, polypropylene terephthalate, polybutylene terephthalate, polyethylene isophthalate, polycyclohexanedimethanol terephthalate, polybutylene naphthalate, polycyclohexanedimethanol naphthalate, poly(ethylene vinyl alcohol), polyacrylonitrile, polyvinyl chloride, poly(vinylidene dichloride), silica, polyamides, nylon, MXD6, or copolymers or blends thereof.

The oxygen scavenging compositions are particularly useful in producing beverage bottles, such as blown or molded beverage bottles, the fabrication of which is a well developed art. One illustrative example of a rigid container according to the present invention is a rigid bottle having a bottle wall comprised of at least a three-layer structure. The three-layer structure in accordance with this aspect of the invention comprises an inner layer and an outer layer, both being comprised of polyesters or copolyesters, preferably aromatic polyesters or copolyesters, and a core layer between the inner and outer layers, the core layer being comprised of an oxygen scavenging layer made from an oxygen scavenging composition disclosed herein.

Rigid containers having multi-layered structures are preferably produced by coextrusion. For example, one layer of an oxygen scavenging composition described herein can be coextruded with two layers of polyester or copolyester, e.g., PET, PEN, and the like. Although coextrusion will typically be preferred for producing the rigid containers described herein, other

approaches available within the art and can also be used, e.g., coating with solutions, heat fusion of separate layers, etc.

It is an advantage of this invention that the adhesion between the oxygen
5 scavenging core layer and the inner and outer polyester layers is sufficiently strong that a tie layer will not generally be needed. However, if desired or necessary for a given implementation of the invention, additional non-polyester layers can be incorporated into the multi-layer structures to improve adhesion, improve barrier properties, reduce costs, etc.

10


The oxygen scavenging compositions can be used as the sole polymeric material from which one or more layers of a container are formed (i.e., the film can be a multilayer structure), it can be blended with other polymeric oxygen
15 scavenging agents (such as polybutadiene) or it can be blended with one or more diluent polymers which are known to be useful in the formation of packaging containers and which often can render the resultant material more processable. Suitable diluent polymers include, but are not limited to, polyethylene such as, for example, low density polyethylene, very low density polyethylene, ultra-low density polyethylene, high density polyethylene, and
20 linear low density polyethylene; polyesters such as, for example, polyethylene terephthalate (PET); polyvinyl chloride (PVC); polyvinylidene chloride (PVDC); and ethylene copolymers such as ethylene/vinyl acetate copolymer, ethylene/alkyl (meth)acrylate copolymers, ethylene/(meth)acrylic acid copolymers, and ionomers. Blends of different diluent polymers also can be
25 used.

Oxygen scavenger compositions useful in the context of this invention, as well as methods for their preparation, have been described in U.S. Patent Application No. 09/127,316, the disclosure of which is incorporated herein by
30 reference in its entirety.

003499-091800

The oxygen scavenging compositions used in producing the rigid containers according to the invention broadly comprise (a) a polymer backbone, preferably an ethylenic backbone; (b) cyclic olefinic pendent groups; and (c) a transition metal catalyst. Optionally, the composition further comprises linking groups linking the backbone with the pendent groups. The polymer composition can also optionally contain alkyl acrylate pendant groups, e.g., methyl acrylate pendant groups.

In certain illustrative embodiments of the invention, the polymeric backbone of the oxygen scavenging compositions is ethylenic and the linking groups are selected from the group consisting of:




wherein R is hydrogen or an alkyl group selected from the group consisting of methyl, ethyl, propyl and butyl groups and where n is an integer in the range from 1 to 12.

In additional embodiments of the invention, the cyclic olefinic pendent groups of the above compositions have the structure (II):

20

(II)




where q_1 , q_2 , q_3 , q_4 , and r are selected from the group consisting of -H, -CH₃, and -C₂H₅; and where m is -(CH₂)_n- with n being an integer in the range from 0 to 4; and wherein, when r is -H, at least one of q_1 , q_2 , q_3 and q_4 is -H.

In still other embodiments of the invention, the polymeric backbone, linking groups and cyclic olefinic pendent groups of the above compositions comprise repeating units, each unit having a structure (III) as follows:

(III)


5



10 wherein $P+T+Q$ is 100 mol % of the total composition; P is greater than 0 mol % of the total composition; Z is selected from the group consisting of an aryl group; $-(C=O)OR_1$; $-O(C=O)R_1$; and an alkyl aryl group, structure (IV):

(IV)

15



20 where R_4 is selected from the group consisting of $-CH_3$, $-C_2H_5$, and $-H$; R_1 is selected from the group consisting of $-H$, $-CH_3$, $-C_2H_5$, $-C_3H_7$ and $-C_4H_9$; R_2 and R_3 are selected from the group consisting of $-H$ and $-CH_3$; X is selected from the group consisting of $-O-$, $-NH-$, $-(C=O)O-$, $-(C=O)NH-$, $-(C=O)S-$, $-O(C=O)-$ and $-(CHR)_\lambda-$; λ is an integer in the range from 1 to 6; Y is $-(CHR)_n-$, where n is an integer in the range from 0 to 12, R being selected from the group consisting of $-H$, $-CH_3$ and $-C_2H_5$; where q_1 , q_2 , q_3 , q_4 , and r are selected from the group consisting of $-H$, $-CH_3$, and $-C_2H_5$; and where m is $-(CH_2)_n-$ and where n is an integer in the range from 0 to 4; and wherein when r is $-H$, at least one of q_1 , q_2 , q_3 and q_4 is $-H$.

25

In other embodiments of the invention, the cyclic olefinic pendent groups of the above compositions and rigid containers are selected from the group consisting of cyclohexene-4-methylene radical, 1-methyl cyclohexene-4-methylene radical, 2-methyl cyclohexene-4-methylene radical, 5-methyl

30

- cyclohexene-4-methylene radical, 1,2-dimethyl cyclohexene-4-methylene radical, 1,5-dimethyl cyclohexene-4-methylene radical, 2,5-dimethyl cyclohexene-4-methylene radical, 1,2,5-trimethyl cyclohexene-4-methylene radical, cyclohexene-4-ethylene radical, 1-methyl cyclohexene-4-ethylene radical, 2-methyl cyclohexene-4-ethylene radical, 5-methyl cyclohexene-4-ethylene radical, 1,2-dimethyl cyclohexene-4-ethylene radical, 1,5-dimethyl cyclohexene-4-ethylene radical, 2,5-dimethyl cyclohexene-4-ethylene radical, 1,2,5-trimethyl cyclohexene-4-ethylene radical, cyclohexene-4-propylene radical, 1-methyl cyclohexene-4-propylene radical, 2-methyl cyclohexene-4-propylene radical, 5-methyl cyclohexene-4-propylene radical, 1,2-dimethyl cyclohexene-4-propylene radical, 1,5-dimethyl cyclohexene-4-propylene radical, 2,5-dimethyl cyclohexene-4-propylene radical, and 1,2,5-trimethyl cyclohexene-4-propylene radical.
- 15 In additional embodiments, the oxygen scavenging polymers further comprise alkyl acrylate pendant groups in addition to the cyclic olefinic pendant groups. Therefore, the polymer compositions can include copolymers of ethylene and acrylic or methacrylic esters of linear, branched or cyclic alkanols having, for example, 1-28 carbon atoms, or terpolymers further containing the cyclic
- 20 olefinic pendant groups described herein.

In a preferred embodiment, the polymer comprises an ethylenic backbone having both alkyl acrylate and cyclic olefinic pendant groups linked to the ethylenic backbone. Such polymers are also referred to as ethylene/alkyl

25 acrylate/cyclohexenyl alkyl acrylate terpolymers. One particularly preferred polymer comprises an ethylene/methyl acrylate/cyclohexenyl methyl acrylate terpolymer, referred to as EMCM.

The oxygen scavenging compositions may be polymeric in nature or they may

30 be lower molecular weight materials. For most rigid bottle applications, the

oxygen scavenging compositions will be polymeric in nature and have molecular weights greater than about 2000 Da. In any case, they may be blended with further polymers or other additives, if desired, to best suit the needs of a given implementation. In the case of low molecular weight materials they will most likely be compounded with a carrier resin before use.

The oxygen scavenging compositions of the present invention will generally further include a transition metal compound as an oxygen scavenger catalyst. The transition metal catalyst can be a salt which includes a metal selected from the first, second, or third transition series of the Periodic Table. The metal preferably is Rh, Ru, or one of the elements in the series of Sc to Zn (i.e., Sc, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, and Zn), more preferably at least one of Mn, Fe, Co, Ni, and Cu, and most preferably Co. Suitable anions for such salts include, but are not limited to, chloride, acetate, oleate, stearate, palmitate, 2-ethylhexanoate, neodecanoate, and naphthenate. Representative salts include cobalt (II) 2-ethylhexanoate, cobalt oleate, and cobalt (II) neodecanoate. (The metal salt also can be an ionomer, in which case a polymeric counterion is employed.)

When used in forming a packaging article, the oxygen scavenging composition of the present invention can include only the above-described polymers and a transition metal catalyst. However, photoinitiators can be added to further facilitate and control the initiation of oxygen scavenging properties. Adding a photoinitiator or a blend of photoinitiators to the oxygen scavenging composition can be preferred, especially where antioxidants have been added to prevent premature oxidation of the composition during processing and storage.

Suitable photoinitiators are known to those skilled in the art. See, e.g., PCT Publication WO 97/07161, WO 97/44364, WO 98/51758, and WO 98/51759,

the teachings of which are incorporated herein by reference as if set forth in full. Specific examples of suitable photoinitiators include, but are not limited to, benzophenone, and its derivatives, such as methoxybenzophenone, dimethoxybenzophenone, dimethylbenzophenone, diphenoxybenzophenone, allyloxybenzophenone, diallyloxybenzophenone, dodecyloxybenzophenone, dibenzosuberone, 4,4'-bis(4-isopropylphenoxy)benzophenone, 4-morpholinobenzophenone, 4-aminobenzophenone, tribenzoyl triphenylbenzene, tritoluoyl triphenylbenzene, 4,4'-bis(dimethylamino)-benzophenone, acetophenone and its derivatives, such as, o-methoxyacetophenone, 4'-methoxyacetophenone, valerophenone, hexanophenone, α -phenyl-butyrophenone, p-morpholinopropiophenone, benzoin and its derivatives, such as, benzoin methyl ether, benzoin butyl ether, benzoin tetrahydropyranyl ether, 4-o-morpholinodeoxybenzoin, substituted and unsubstituted anthraquinones, α -tetralone, acenaphthenequinone, 9-acetylphenanthrene, 2-acetyl-phenanthrene, 10-thioxanthenone, 3-acetylphenanthrene, 3-acetylinole, 9-fluorenone, 1-indanone, 1,3,5-triacetylbenzene, thioxanthen-9-one, isopropylthioxanthen-9-one, xanthene-9-one, 7-H-benz[de]anthracen-7-one, 1'-acetophenone, 2'-acetophenone, acetophenone, benz[de]anthracen-7-one, 1'-acetophenone, 2'-acetophenone, acetophenone, benz[a]anthracene-7,12-dione, 2,2-dimethoxy-2-phenylacetophenone, α,α -diethoxyacetophenone, α,α -dibutoxyacetophenone, 4-benzoyl-4'-methyl(diphenyl sulfide) and the like. Single oxygen-generating photosensitizers such as Rose Bengal, methylene blue, and tetraphenylporphine as well as polymeric initiators such as poly(ethylene carbon monoxide) and oligo[2-hydroxy-2-methyl-1-[4-(1-methylvinyl)phenyl]propanone] also can be used. However, photoinitiators are preferred because they generally provide faster and more efficient initiation. When actinic radiation is used, photoinitiators can provide initiation

at longer wavelengths which are less costly to generate and present less harmful side effects than shorter wavelengths.

Photoinitiators that are especially useful in the present invention include
5 benzophenone derivatives containing at least two benzophenone moieties, as described in copending U.S. patent application 08/857,325, filed May 16, 1997. These compounds act as effective photoinitiators to initiate oxygen scavenging activity in oxygen scavenging compositions. Such benzophenone derivatives have a very low degree of extraction from oxygen barrier
10 compositions, which may lead to reduced malodor or off-taste of a packaged food, beverage, or oral pharmaceutical product by extracted photoinitiator.

A "benzophenone moiety" is a substituted or unsubstituted benzophenone group. Suitable substituents include alkyl, aryl, alkoxy, phenoxy, and alicyclic
15 groups contain from 1 to 24 carbon atoms or halides.

The benzophenone derivatives include dimers, trimers, tetramers, and oligomers of benzophenones and substituted benzophenones.

20 The benzophenone photoinitiators are represented by the formula:



wherein A is a bridging group selected from sulfur; oxygen; carbonyl; $-\text{SiR}''_2-$,
25 wherein each R'' is individually selected from alkyl groups containing from 1 to 12 carbon atoms, aryl groups containing 6 to 12 carbon atoms, or alkoxy groups containing from 1 to 12 carbon atoms; $-\text{NR}'''$ -, wherein R''' is an alkyl group containing 1 to 12 carbon atoms, an aryl group containing 6 to 12 carbon atoms, or hydrogen; or an organic group containing from 1 to 50

carbon atoms; a is an integer from 0 to 11; B is a substituted or unsubstituted benzophenone group; and b is an integer from 2 to 12.

5 The bridging group A can be a divalent group, or a polyvalent group with 3 or more benzophenone moieties. The organic group, when present, can be linear, branched, cyclic (including fused or separate cyclic groups), or an arylene group (which can be a fused or non-fused polyaryl group). The organic group can contain one or more heteroatoms, such as oxygen, nitrogen, phosphorous, silicon, or sulfur, or combinations thereof. Oxygen
10 can be present as an ether, ketone, ester, or alcohol.

The substituents of B, herein R", when present, are individually selected from alkyl, aryl, alkoxy, phenoxy, or alicyclic groups containing from 1 to 24 carbon atoms, or halides. Each benzophenone moiety can have from 0 to 9
15 substituents. Substituents can be selected to render the photoinitiator more compatible with the oxygen scavenging composition.

Examples of such benzophenone derivatives comprising two or more benzophenone moieties include dibenzoyl biphenyl, substituted dibenzoyl
20 biphenyl, benzoylated terphenyl, substituted benzoylated terphenyl, tribenzoyl triphenylbenzene, substituted tribenzoyl triphenylbenzene, benzoylated styrene oligomer (a mixture of compounds containing from 2 to 12 repeating styrenic groups, comprising dibenzoylated 1,1-diphenyl ethane, dibenzoylated 1,3-diphenyl propane, dibenzoylated 1-phenyl naphthalene, dibenzoylated
25 styrene dimer, dibenzoylated styrene trimer, and tribenzoylated styrene trimer), and substituted benzoylated styrene oligomer. Tribenzoyl triphenylbenzene and substituted tribenzoyl triphenylbenzene are especially preferred.

When a photoinitiator is present, it can enhance and/or facilitate the initiation of oxygen scavenging by the composition of the present invention upon exposure to radiation. The amount of photoinitiator can depend on the amount and type of cyclic unsaturation present in the polymer, the wavelength and intensity of radiation used, the nature and amount of antioxidants used, and the type of photoinitiator used. The amount of photoinitiator also can depend on how the scavenging composition is used. For instance, if a photoinitiator-containing composition is in a film layer, which underneath another layer is somewhat opaque to the radiation used, more initiator might be needed. However, the amount of photoinitiator used for most applications ranges from about 0.01 to about 10% (By wt.) of the total composition. Oxygen scavenging can be initiated by exposing an article containing the composition of the present invention to actinic or electron beam radiation.

One or more antioxidants can be incorporated into the scavenging composition of the present invention to retard degradation of the components during compounding and rigid container formation. Although such additives prolong the induction period for oxygen scavenging activity to occur in the absence of irradiation, the layer or article (and any incorporated photoinitiator) can be exposed to radiation at the time oxygen scavenging properties are required. Suitable antioxidants include 2,6-di(t-butyl)-4-methylphenol(BHT), 2,2'-methylene-bis(6-t-butyl-p-cresol), triphenylphosphite, tris-(nonylphenyl)phosphite, dilaurylthiodipropionate, vitamin E (α -tocopherol), octadecyl 3,5,-di-tert-butyl-4-hydroxyhydrocinnamate, tetrakis[methylene(3,5-di-tert-butyl-4-hydroxyhydrocinnamate)]methane and the like.

When an antioxidant is included as part of the composition of the present invention, it preferably is present in an amount which prevents oxidation of the

10

15

25

while the amount of transition metal catalyst affects the rate at which oxygen is consumed as well as the induction period.

5 The composition of the present invention can provide oxygen scavenging properties at a desirable rate and capacity while having good processing and compatibility properties relative to compositions including conventional non-cyclic ethylenically unsaturated polymers. Thus, the present composition can be used to provide, by itself or as a blend with diluent film-forming polymers such as polyolefins and the like, a rigid container that can be manufactured
10 and processed easily. Further, the subject oxygen scavenging composition will deplete the oxygen within a package cavity without substantially detracting from the color, taste, and/or odor of the product contained therein.

15 The amount of the polymeric scavenging component contained in the subject composition can range from about 1 to almost about 100%, preferably from about 5 to about 97.5%, more preferably from about 10 to 95%, even more preferably from about 15 to about 92.5%, still more preferably from about 20 to about 90%, (with all the foregoing percentages being by weight) of the composition or layer made therefrom. Typically, the amount of transition
20 metal catalyst can range from 0.001 to 1% (by wt.) of the scavenging composition, based on the metal content only (i.e., excluding ligands, counterions, etc.). Where one or more other scavenging compounds and/or diluent polymers are used as part of the composition, such other materials can make up as much as 99%, preferably up to about 75%, by weight of the
25 scavenging composition. Any further additives employed normally do not make up more than 10%, preferably no more than about 5%, by weight of the scavenging composition.

One embodiment of the invention provides for including a photoinitiator as
30 part of the subject oxygen scavenging composition and subjecting a rigid

008T60" 2564990

article that includes such a composition to radiation so as to initiate oxygen scavenging at desired rates.

- 5 The initiating radiation preferably is actinic, e.g., UV or visible light having a wavelength of from about 200 to about 750 nm, preferably of from about 200 to 600 nm, and most preferably from about 200 to 400 nm. Such light can be delivered in a continuous or pulsed manner. The rigid article containing the oxygen scavenging composition preferably is exposed to such radiation until it receives at least about 0.01 J/g of radiation, more preferably until it receives a
- 10 dose in the range of about 0.1 to about 500 J/g. The radiation also can be electron-beam radiation at a dosage of at least about 2 kiloGray (kG), preferably from about 10 to about 100 kG. Other potential sources of radiation include ionizing radiation such as gamma, X-ray, and corona discharge. Duration of exposure depends on several factors including, but
- 15 not limited to, the amount and type of photoinitiator present, thickness of the layers to be exposed, thickness and opacity of intervening layers, amount of any antioxidant present, and the wavelength and intensity of the radiation source.
- 20 When using oxygen scavenging layers or articles, irradiation can occur during or after the layer or article is prepared. If the resulting layer or articles is to be used to package an oxygen sensitive product, exposure can be just prior to, during, or after packaging. For best uniformity of radiation, exposure preferably occurs at a processing stage where the layer or article is in the
- 25 form of a flat sheet. For further information on initiation via irradiation, the reader is directed to PCT publications WO 98/05555 and WO 98/05703, as well as PCT 97/13598, 97/13370, 97/13369, the teachings of which are incorporated herein by reference.

Determining the oxygen scavenging rate and capacity of a given oxygen scavenging composition contemplated for a particular use can be beneficial. To determine the rate, the time elapsed before the scavenger depletes a certain amount of oxygen from a sealed container is measured. In some instances, the rate can be determined adequately by placing a film containing the desired scavenging composition in an air-tight, sealed container of an oxygen containing atmosphere, e.g., air which typically contains 20.6% (by vol.) O₂. Over time, samples of the atmosphere inside the container are removed to determine the percentage of oxygen remaining. (Usually, the specific rates obtained vary under different temperature and atmospheric conditions. Atmospheres having lower initial oxygen content and/or maintained under low temperature conditions provide a more stringent test of the scavenging ability and rate of a composition. The rates which follow are at room temperature and one atmosphere of air, unless otherwise specified.)

When an active oxygen barrier is needed, a useful scavenging rate can be as low as about 0.05 cm³ oxygen per gram of the polymer in the scavenging composition per day in air at 25°C and at 1 atm (101.3 kPa). However, in most instances, the present composition has a rate equal to or greater than about 5.8 x 10⁻⁸ cm³/g•s (0.5 cm³/g•day), even up to or greater than about 5.8 x 10⁻⁵ cm³/g•s (5 cm³/g•day). Further, films or layers including the subject composition are capable of a scavenging rate greater than about 1.2 x 10⁻⁴ cm³/m²•s (10 cm³/m²•day) and under some conditions, greater than about 2.9 x 10⁻⁴ cm³/m²•s (25 cm³/m²•day). (Generally, films or layers deemed suitable for use as an active oxygen barrier can have a scavenging rate as low as 1.2 x 10⁻⁵ cm³/m²•s (1 cm³/m²•day) when measured in air at 25°C and 101 kPa (1 atm). Such rates make those layers suitable for scavenging oxygen from within a package, as well as suitable for active oxygen barrier applications.

When the method of the present invention is to be used in an active oxygen barrier application, the initiated oxygen scavenging activity, in combination with any oxygen barriers, preferably creates an overall oxygen permeance of less than about $1.1 \times 10^{-10} \text{ cm}^3/\text{m}^2 \cdot \text{s} \cdot \text{Pa}$ ($1.0 \text{ cm}^3/\text{m}^2 \cdot \text{day} \cdot \text{atm}$) at 25°C . The oxygen scavenging capacity preferably is such that this value is not exceeded for at least two days.

Once scavenging has been initiated, the scavenging composition, layer, or article prepared therefrom preferably is able to scavenge up to its capacity, i.e., the amount of oxygen which the scavenger is capable of consuming before it becomes ineffective. In actual use, the capacity required for a given application can depend on the quantity of oxygen initially present in the package, the rate of oxygen entry into the package in the absence of the scavenging property, and the intended shelf life for the package. When using scavengers that include the composition of the present invention, the capacity can be as low as $1 \text{ cm}^3/\text{g}$, but can be $50 \text{ cm}^3/\text{g}$ or higher.

In a rigid container having polyester or copolyester oxygen barrier layers, it is preferable that the combination of oxygen barriers and the oxygen scavenging layers create an overall oxygen transmission rate of less than about 1.0 cubic centimeter-mil per square meter per day per atmosphere pressure at 25°C . Another definition of acceptable oxygen scavenging is derived from testing actual packages. In actual use, the scavenging rate requirement will largely depend on the internal atmosphere of the package, the contents of the package and the temperature at which it is stored.

The scavenging rate of the rigid article will depend primarily on the amount and nature of the oxygen scavenging composition in the article, and secondarily on the amount and nature of other additives (e.g., diluent polymer, antioxidant, etc.) which are present in the scavenging component,

as well as the overall manner in which the container is fabricated, e.g., surface area/volume ratio.

5 The oxygen scavenging capacity of rigid container of the invention can be measured by determining the amount of oxygen consumed until the article becomes ineffective as a scavenger. The scavenging capacity of the package will depend primarily on the amount and nature of the scavenging moieties present in the article. Alternatively, the effectiveness of an oxygen scavenging polymer can be determined from the oxygen transmission rate
10 through the film. An effective oxygen scavenging polymer should be able to block most, if not all, oxygen transmission through the film.

The following examples are provided to demonstrate certain illustrative embodiments of this invention. It should be appreciated by those skilled in
15 the art that the techniques disclosed in the examples which follow represent those found by the inventors to function in the practice of the invention and thus can be considered to constitute examples of illustrative modes for its practice. However, those skilled in the art should, in light of the present disclosure, appreciate that many changes can be made in the specific
20 embodiments which are disclosed and still obtain a like or similar result without departing from the spirit and scope of the invention.

EXAMPLES

Objects and advantages of this invention are further illustrated by the
25 following examples. The particular materials and amounts thereof, as well as other conditions and details, recited in these examples should not be used to unduly limit this invention.

Example 1: Preparation of EMCM

The preparation of EMCM and like polymers has been described, for example in U.S. Patent Application Serial No. 09/127,316, the disclosure of which is incorporated herein by reference in its entirety.

5

In one example, 600 ml of decalin was placed in a flask. To this was added 334 grams of Chevron SP-2260 (0.9330 moles of methyl acrylate) and 0.44 g of Irganox® 1010 (0.1% mole). The temperature of the mixture was gradually raised while stirring. When the temperature reached approximately 120°C, 104.6 g (0.93 moles) of cyclohex-1-ene-4-methanol was added. When the temperature reached approximately 140°C, 4.4 g of the catalyst $\text{Ti}(\text{OC}_2\text{H}_5)_4$ was added a portion at a time. The temperature was maintained at 160°C while stirring. The course of the reaction was observed by subjecting samples of the mixture to NMR at hourly intervals. The percent conversion is given in Table 2 below. After 3 hours of reaction, the mixture was cooled and 400 ml of CHCl_3 was added and the mixture was then precipitated by adding it to 4 liters of CH_3OH in a Waring blender. The precipitate was filtered and washed with CH_3OH and dried in a vacuum oven at 50°C. The dried mixture yielded 380.5 g of polymer.

20

Table 2

Time (hours)	Percent Conversion
1 hour	43.8%
2 hours	56.7%
3 hours	55.7%

25

185 grams of the above-prepared polymer was combined with 45 ml normal hexane and 1.54 g cobalt-neodecanoate resulting in 1000 ppm of cobalt ion and 0.0185 g Irganox® 1010 resulting in 100 ppm Irganox®. The mixture was heated and blended and then dried in a vacuum-oven. The resulting compound was extruded into a film.

Additionally, 185 grams of the above-prepared polymer was combined with 45 ml normal hexane and 1.54 g cobalt-neodecanoate (resulting in 1000 ppm of cobalt ion) and 0.046 g Irganox® 1010 (resulting in 250 ppm Irganox®). The mixture is heated and blended and then dried in a vacuum-oven. The
5 resulting compound is extruded into a film.

In another example, ethylene-methyl acrylate copolymer (EMAC) was fed into a Werner & Pfleiderer ZSK-30 twin screw extruder at 6 kg/hr, and the reactants and catalysts were added to the extruder in a subsequent reaction
10 zone. The catalyst $\text{Ti}(\text{OC}_3\text{H}_7)_4$ was added with the reactants at 3 mol % or at a rate of 148 cc/hr. Irganox®/Toluene solution was added at 4.5 g/900 cc using a Milton Roy 29/290 mini-pump. To obtain 100 ppm of Irganox®, it must be added at 2.2 cc/min. To obtain 50 ppm of Irganox, it must be added at 1.1 cc/min. Cyclohexane methyl alcohol with 1,000 ppm of an antioxidant of
15 BHT was added via a Milton Roy dual head at 1958 cc/hr. Steam is injected into the system at 800 cc $\text{H}_2\text{O}/\text{Hr}$ at the end of the reaction zone.

51 lbs of EMCM product (100 ppm Irganox® 1010, 59.3% methyl alcohol (MA), 2.98 g/10 min. Melt Flow) was produced over a period of approximately
20 2 hours.

In another example, 45 lbs of EMCM product (100 ppm Irganox®1010, 2.38 g/10 min Melt Index) was extruded over a period of approximately 3 hours. A dual steam stripping setup was used in which pressurized injectors
25 at zones 4 and 11 of the extruder pumped steam at 1076 cc/hr and 728 cc/hr, respectively. Both injectors were Pulse 680 pumps with a pressure of at least 800 psi, except at the first measured time interval when injector (No. 4) was measured at 500-550 psi and injector (No. 11) was measured at 500 psi.

0034760" E6549960

Example 2: Preparation of PET/EMCM/PET rigid multi-layer structures

Multilayer films were made on a Randcastle extruder. Commercial bottle grade PET was dried at about 150°C for about 3 hours in a vacuum oven. The oxygen scavenging polymer was compounded on a Haake twin screw
5 extruder at 170 °C from 90 wt.% EMCM and 10 wt.% EMAC based cobalt masterbatch (containing 1 wt.% BBP³ photoinitiator and 1 wt.% cobalt as cobalt oleate). The feedblock for PET was set to 265-290°C and that for oxygen scavenging polymer was set to 170-180°C. The die temperature was set to 265-290°C.

10

Oxygen transmission testing was done on a Mocon Ox-Trans 2/20 ML system at 23 °C. Nitrogen containing 2% hydrogen was used as carrier gas to flush both sides of the film at 10 cc/min flow rate for 1-4 hrs before testing. Air was used as test gas at 10 cc/min flow rate.

15

Tests were performed using Mylar film, unoriented monolayer film made from bottle grade PET, PET/OSP/PET unoriented 3-layer films tested as is, and PET/OSP/PET unoriented 3-layer films tested after a 10 minute exposure to UV light (~254nm). The following results were obtained.

20

008760" 2664960

OTR Data for EMCM/PET Multilayer Films

Film	Thickness (mil)	Oxygen Transmission Rate (ccO ₂ /m ² /day)
Mylar film (oriented commercial PET film)	0.92	35-60
Unoriented film made from Bottle Grade PET	2.0	132
PET/OSP/PET 3-layer film Unoriented, tested as is	3.8 (1/2/1)	165
PET/OSP/PET 3-layer film Unoriented, tested after 10 min to 254 nm UV at 1 inch to receive 5 J/cm ² **	3.8 (1/2/1)	0-6*

OSP: EMCM with 10% Co masterbatch.

*3 out of 4 readings were 0, and 1 out of 4 was 6 ccO₂/m²/day.

- 5 ** PET outlayer film will block most of the UV light, it is estimated that the OSP core layer will receive about 100 mJ/ cm² UV light.

Example 3

- A PET/OSP/PET multilayer structure is made essentially as described in
- 10 Example 2, except that the film is UV triggered with Mercury Arc UV lamp with long wavelength, e.g., 355 nm - 375 nm, before OTR test.

Example 4

- A PET/OSP/PET multilayer structure is made essentially as described in
- 15 Example 2, except that the film is made with a core layer containing 90 wt.% EMCM and 10 wt.% cobalt masterbatch which contains 1 wt.% cobalt as cobalt oleate and 1 wt.% of Irgacure 369, Irgacure 500 , Irgacure 651,

008760" 2564960

Irgacure 819, Irgacure 1700, Irgacure 4265 (all available from Ciba Corporation), or TPO (available from BASF).

Example 5

- 5 A PET/OSP/PET multilayer structure is made essentially as described in Example 2, except that the film is made with a core layer containing 90 wt.% EMCM and 10 wt.% cobalt masterbatch which contains 1 wt.% cobalt as cobalt oleate and no photoinitiator.

10 Example 6

- A PET/OSP/PET multilayer structure is made essentially as described in Example 2, except that the film is made with a core layer containing 90 wt.% EMCM and 10 wt.% cobalt masterbatch which contains 1 wt.% cobalt as cobalt octoate and no photoinitiator. The cobalt masterbatch is heat treated at 150-200°C before it is used for making the film.

Example 7

- A PET/OSP/PET multilayer structure is made essentially as described in Example 2, except that the film is made with a core layer containing 90 wt.% EMCM and 10 wt.% cobalt masterbatch which contains 1 wt.% cobalt as cobalt stearate and no photoinitiator. The cobalt masterbatch is heat treated at 150-200°C before it is used for making the film.

Example 8

- 25 A PET/OSP/PET multilayer structure is made essentially as described in Example 2, except that the film is made with a core layer containing 90 wt% EMCM and 10 wt% cobalt masterbatch which contains 1 wt% cobalt as cobalt stearate, and no photoinitiator. The cobalt masterbatch is used as is without any heat or other treatment.

Example 9

A PET/OSP/PET multilayer structure is made essentially as described in Example 2, except that the film is made with a core layer containing 45 wt.% of EVOH, 45 wt.% EMCM and 5 wt.% cobalt masterbatch which contains 1
5 wt.% cobalt as cobalt oleate and 1 wt.% of Irgacure 819.

Example 10

A PET/OSP/PET multilayer structure is made essentially as described in Example 2, except that the film is made with a core layer containing 45 wt.%
10 of EVOH, 45 wt.% EMCM and 5 wt.% cobalt masterbatch which contains 1 wt.% cobalt as cobalt oleate and no photoinitiator. The cobalt masterbatch is heat treated at 150-200°C before it is used for making the film.


Also included within these examples and the scope of the invention are
15 compositions comprising various combinations of these substances and materials.

Aspects of the present invention have been described by way of example only and it should be appreciated that modifications and additions may be made
20 thereto without departing from the scope thereof.

WHAT IS CLAIMED:


1. A multi-layer rigid container for food or beverage packaging comprising at least an inner layer, an outer layer and a core layer between the inner layer and the outer layer, wherein the inner and outer layers are comprised of an aromatic polyesters or copolyesters, and wherein the core layer is comprised of an oxygen scavenging composition comprising (a) a polymer backbone; (b) cyclic olefinic pendent groups covalently linked to the polymer backbone; and (c) a transition metal catalyst.
2. The rigid container of claim 1, wherein the inner layer and the outer layer comprise aromatic polyesters or copolyesters selected from the group consisting of polyethylene terephthalate, polyethylene naphthalate, polypropylene terephthalate, polybutylene terephthalate, polyethylene isophthalate, polycyclohexanedimethanol terephthalate, polybutylene naphthalate and polycyclohexanedimethanol naphthalate, and copolymers and blends thereof.
3. The rigid container of claim 1, wherein the polymer backbone is ethylenic and the cyclic olefinic pendant groups are linked to the polymer backbone by linking groups selected from the group consisting of:
 $-O-(CHR)_n-$; $-(C=O)-O-(CHR)_n-$; $-NH-(CHR)_n-$; $-O-(C=O)-(CHR)_n-$;
 $-(C=O)-NH-(CHR)_n-$; and $-(C=O)-O-CHOH-CH_2-O-$;
 wherein R is hydrogen or an alkyl group selected from the group consisting of methyl, ethyl, propyl and butyl groups and where n is an integer in the range from 1 to 12.
4. The rigid container of claim 1, wherein the cyclic olefinic pendent groups have the structure (II):

(II)




where q_1 , q_2 , q_3 , q_4 , and r are selected from the group consisting of $-H$, $-CH_3$, and $-C_2H_5$; and where m is $-(CH_2)_n-$ with n being an integer in the range from 0 to 4; and wherein, when r is $-H$, at least one of q_1 , q_2 , q_3 and q_4 is $-H$.

5. The rigid container of claim 3, wherein the polymeric backbone, linking groups and cyclic olefinic pendent groups comprise repeating units, each unit having a structure (III) as follows:



wherein $P+T+Q$ is 100 mol % of the total composition; P is greater than 0 mol % of the total composition; Z is selected from the group consisting of an aryl group; $-(C=O)OR_1$; $-O(C=O)R_1$; and an alkyl aryl group, structure (IV):



where R_4 is selected from the group consisting of $-CH_3$, $-C_2H_5$, and $-H$; R_1 is selected from the group consisting of $-H$, $-CH_3$, $-C_2H_5$, $-C_3H_7$ and $-C_4H_9$; R_2 and R_3 are selected from the group consisting of $-H$ and $-CH_3$; X is selected from the group consisting of $-O-$, $-NH-$, $-(C=O)O-$, $-(C=O)NH-$, $-(C=O)S-$, $-O(C=O)-$ and $-(CHR)_\lambda-$; λ is an integer in the range from 1 to 6; Y is $-(CHR)_n-$, where n is an integer in the range from 0 to 12, R being selected from the group

consisting of $-H$, $-CH_3$ and $-C_2H_5$; where q_1 , q_2 , q_3 , q_4 , and r are selected from the group consisting of $-H$, $-CH_3$, and $-C_2H_5$; and where m is $-(CH_2)_n-$ and where n is an integer in the range from 0 to 4; and wherein when r is $-H$, at least one of q_1 , q_2 , q_3 and q_4 is $-H$.

5

6. The rigid container of claim 1, wherein the cyclic olefinic pendent group is selected from the group consisting of cyclohexene-4-methylene radical, 1-methyl cyclohexene-4-methylene radical, 2-methyl cyclohexene-4-methylene radical, 5-methyl cyclohexene-4-methylene radical, 1,2-dimethyl cyclohexene-4-methylene radical, 1,5-dimethyl cyclohexene-4-methylene radical, 2,5-dimethyl cyclohexene-4-methylene radical, 1,2,5-trimethyl cyclohexene-4-methylene radical, cyclohexene-4-ethylene radical, 1-methyl cyclohexene-4-ethylene radical, 2-methyl cyclohexene-4-ethylene radical, 5-methyl cyclohexene-4-ethylene radical, 1,2-dimethyl cyclohexene-4-ethylene radical, 1,5-dimethyl cyclohexene-4-ethylene radical, 2,5-dimethyl cyclohexene-4-ethylene radical, 1,2,5-trimethyl cyclohexene-4-ethylene radical, cyclohexene-4-propylene radical, 1-methyl cyclohexene-4-propylene radical, 2-methyl cyclohexene-4-propylene radical, 5-methyl cyclohexene-4-propylene radical, 1,2-dimethyl cyclohexene-4-propylene radical, 1,5-dimethyl cyclohexene-4-propylene radical, 2,5-dimethyl cyclohexene-4-propylene radical, and 1,2,5-trimethyl cyclohexene-4-propylene radical.

7. The rigid container of claim 1, wherein the oxygen scavenging composition is selected from the group consisting of a ethylene/methyl acrylate/cyclohexenyl methyl acrylate terpolymer, a cyclohexenyl methyl acrylate/ethylene copolymer, a cyclohexenyl methyl methacrylate/styrene copolymer, a cyclohexenyl methyl acrylate homopolymer and a methyl acrylate/cyclohexenyl methyl acrylate copolymer.

ABSTRACT OF THE DISCLOSURE

Rigid containers are provided comprising oxygen scavenger compositions that produce only low levels of volatiles or by-products as a consequence of oxygen scavenging. In particular, a family of polymers
5 containing selected cyclic olefinic pendent groups are used in the rigid containers to achieve oxygen scavenging that is associated with minimal or no organoleptic by-products after oxidation.

0965493-091800
008160-2664960